FM 2108

Avery Dennison™ FM 2108 is a 130 mil double coated white polyethylene foam with a high shear rubber adhesive. It bonds to a wide variety of low surface energy materials and features high shear strength and the ability to fill gaps. FM 2108 is commonly used in general industrial foam applications.

FEATURES

- Double coated tape construction
- High shear rubber adhesive
- Polyethylene foam carrier
- · Super calendered kraft release liner



BENEFITS

- · Dimensional stability and good die cutting characteristics
- Strong bond to a wide variety of low surface energy materials
- High shear and high temperature resistance
- Gap filling properties and good conformability
- High tensile strength and tear resistance with excellent die cutting performance
- Two-year warranty

CONSTRUCTION:

Liner:

60# White Kraft

Adhesive 1:

Rubber

Carrier:

Polyethylene Foam

Adhesive 2:

Rubber



FM 2108

Adhesive Properties:

Thickness	ASTM D3652	US Mils	MM's	Micron's (µm)
Liner		3.5	0.09	89
Adhesive 1 - Liner		2.5	0.06	64
Carrier		125.0	3.18	3175
Adhesive 2 - Unwind		2.5	0.06	64
Total Caliper without I	Liner:	130.0	3.30	3302
Total Caliper:		133.5	3.39	3391
Peel Adhesion	ASTM D3330			
180° 12 in (300 mm)	min @ Room Temp			
Substrate		Lbf / in		N / Meter
SS	Liner 72 hr dwell	4.0		704
	Unwind	4.0		704
	701	4.0		70.4
PP	Liner 72 hr dwell	4.0		704
	Unwind	4.0		704
	Onwind	4.0		704
Loop Tack	ASTM D6195			
180° 32 in (508 mm)	/ min @ Room Temp	11.67		N. (8.5 . (
Substrate	le l	Lbf / in		N / Meter
SS	Liner Initial	6.5		1,145
0.4.1.01	1			
Static Shear	ASTM D3654			
180° 1" sq (6.5 cm2) Substrate	1000 g @ Room Temp	Min to Fail		
Substrate		WIII to Fall		

Typical Values

175° F Maximum Service Temperature THE LISTED VALUES ARE TYPICAL AND NOT INTENDED TO SERVE AS PRODUCT SPECIFICATIONS

APPLICATION TECHNIQUES

Minimum Application Temperature

Minimum Service Temperature

TEMPERATURES

SS

- It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- · Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

24 hr dwell

STORAGE / SHELF LIFE

• Two years when stored at 64-72°F (18-22°C) / 30-70% relative humidity, out of direct sunlight and in original packaging.

Please refer to Tapes. Avery Dennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2020 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



Performance Tapes

Liner

Asia Pacific Kunshan, China, NO. 618 Nanhe Road Kunshan Economic & Technological Zone China, 215335

Phone: +86 512 57155001 Fax: +86 512 57155059

Europe Tieblokkenlaan 1 B-2300 Turnhout Belgium

> 10,000

۰F

50° F

-40° F

Phone: +32 (0)14 40 48 11 Fax: +32 (0)14 40 48 55

North America 250 Chester Street Painesville, Ohio 44077 USA Phone: +1 866-462-8379 Fax: +1 888-358-4469

° C

10° C

-40° C

80° C