


September, 2017

3M™ Low VOC Tape 99015LVC

Product Description

3M™ Low VOC Tapes with Acrylic Adhesive 98010LVC and 99015LVC are designed for automotive interior applications on commonly used foam substrates, such as PU Ester and EPDM, as well as high surface energy (HSE) substrates. The pure acrylic adhesive on both thin bonding tapes is designed to be low fog and low emission to meet the VOC requirements set forth in the JAMA and VDA278 test methods used by Automotive OEM's and tier suppliers.

98010LVC is a 3.9 mil (0.10 mm) low VOC scrim reinforced transfer tape that provides good dimensional stability for large area lamination. 99015LVC is a 5.9 mil (0.15 mm) low VOC double coated tape with tissue carrier for ease of handling during lamination and excellent die-cutting characteristic.



Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Physical Properties

Property	Values	
Adhesive Thickness	0.15 mm	5.9 mil
Liner	58# Densified Kraft	
Liner Thickness	0.08 mm	3.2 mil
Liner Color	White with red print	

Product Testing

JAMA Low VOC Results
Tested by: SGS Institut Fresenius GmbH

Substance	98010LVC Measured VOC (µg/specimen)	99015LVC Measured VOC (µg/specimen)	VOC Targets (µg/specimen)
Formaldehyde	0.12	0.08	<0.3
Acetaldehyde	0.04	0.04	<0.3
Toluene	0.08	0.05	<0.3
Ethylbenzene	<0.04	<0.04	<0.3
Xylene (o-,m-,p-)	<0.04	<0.04	<0.7
Styrene	<0.04	<0.04	<0.3
Tetradecane	<0.04	<0.04	Report
Di-n-butyl phthalate	<0.04	<0.04	Report
Di-2-ethylhexyl phthalate	<0.04	<0.04	Report
Benzene	N/A	N/A	N/A
Acrolein	N/A	N/A	N/A

Test method:
Sample Size: 100mm×100mm
Heating condition: 149°F (65°C) for 2 hours
Gas trapping volume: 4L with Tedlar bag (TOL)
Absorption pipe: Tenax-TA (for volatile carbon oxide), DNPH cartridge (for aldehydes)
Absorb air in Tedlar bag with each absorption pipe after heating and measure with gas chromatograph
mass spectrometer or high speed liquid chromatography

VDA 278 Test Results
Tested by: SGS Institut Fresenius GmbH

Test Parameter	98010LVC	99015LVC
	Measured value (µg/g)	
VOC	16	18
	15	13
FOG	89	110

Note

Calipers are nominal values

Typical Performance Characteristics

Relative High Temperature Operating Ranges		Test Condition
120 °C	250 °F	Short Term (minutes, hours)
90 °C	194 °F	Long Term (days, weeks)

Property: Relative High Temperature Operating Ranges

Typical Performance Characteristics (continued)

90° Peel Adhesion		Dwell/Cure Time	Substrate
6 N/cm	55 oz/in	20 min @ Room Temperature	Stainless Steel
13.8 N/cm	129 oz/in	72 hr @ 158°F(70°C)	Stainless Steel
9.52251975 N/cm	87 oz/in	20 min @ Room Temperature	Polycarbonate (PC)
2.6269020000000003 N/cm	24 oz/in	20 min @ Room Temperature	Polypropylene (PP)
2.07963075 N/cm	19 oz/in	72 hr @ 158°F(70°C)	Polypropylene (PP)
1.9701765 N/cm	18 oz/in	20 min @ Room Temperature	ABS
7.33343475 N/cm	67 oz/in	72 hr @ 158°F(70°C)	ABS

Property: 90° Peel Adhesion
Method: ASTM D3330
Backing: 2 mil Aluminum Foil
notes: 12 in/min (300 mm/min)

180° Peel Adhesion		Dwell/Cure Time	Substrate
13.243964250000001 N/cm	121 oz/in	20 min @ Room Temperature	Stainless Steel
12.258876 N/cm	112 oz/in	72 hr @ 158°F(70°C)	Stainless Steel
2.6269020000000003 N/cm	24 oz/in	20 min @ Room Temperature	Polypropylene (PP)
2.73635625 N/cm	25 oz/in	72 hr @ 158°F(70°C)	Polypropylene (PP)
13.572327 N/cm	124 oz/in	20 min @ Room Temperature	ABS
13.7912355 N/cm	126 oz/in	72 hr @ 158°F(70°C)	ABS
14.010144 N/cm	128 oz/in	20 min @ Room Temperature	Polycarbonate (PC)
14.010144 N/cm	128 oz/in	72 hr @ 158°F(70°C)	Polycarbonate (PC)

Property: 180° Peel Adhesion
Method: ASTM D3330
Backing: 2 mil Aluminum Foil
notes: 12 in/min (300 mm/min)

Property	Values	Method	Test Condition	Notes
Static Shear	10000 min	ASTM D3654	500 g @ 70°C (158°F)	1 in² sample size

Table continued on next page

Typical Performance Characteristics (continued)

Property	Values	Method	Test Condition	Notes
Fogging (Photometric method)	97 %	SAEJ1756	1 hr	The effect of fogging condensate on the glass plate is determined by measuring the 60o specular gloss. The 60o specular gloss for the same glass plate that is free from fogging condensate and carefully cleaned before the test is used as a reference value. The higher value indicates less fogging.
Fogging (Photometric method)	98 %	SAEJ1756	16 hr	The effect of fogging condensate on the glass plate is determined by measuring the 60o specular gloss. The 60o specular gloss for the same glass plate that is free from fogging condensate and carefully cleaned before the test is used as a reference value. The higher value indicates less fogging.

Available Sizes

Property	Values	Values	Notes
Master Width	1000, 1372, 1500 mm	39, 54, 59 in	More sizes may be available. Please call 800-362-3550 or talk to your local 3M representative for more information.

Handling/Application Information

Application Ideas

- Automotive interior bonding
- Door trim and door bolster attachment
- Foam, flock and felt for BSR applications
- Gaskets and seals
- Headliner component and shade attachment
- Acoustic/Thinsulate™ attachment

Storage and Shelf Life

It is suggested that products are stored at room temperature conditions of 70°F (21°C) and 50% relative humidity. Out of direct sunlight. If stored properly, product retains its performance and properties for 24 months from date of manufacture.

Trademarks

3M and Thinsulate are trademarks of 3M Company

References

Property	Values
3m.com Product Page	https://www.3m.com/3M/en_US/company-us/all-3m-products/~-/3M-Low-VOC-Double-Coated-Tissue-Tape-99015LVC/?N=5002385+3291849576&rt=rud
Safety Data Sheet (SDS)	https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=99015LVC

Family Group

	98010LVC	99015LVC
Relative High Temperature Operating Ranges (°C) Test Condition: Short Term (minutes, hours)	120	120
Relative High Temperature Operating Ranges (°C) Test Condition: Long Term (days, weeks)	90	90
Adhesive Thickness (mm)	0.1	0.15
Liner	58# Densified Kraft	58# Densified Kraft
Liner Thickness (mm)	0.08	0.08
Liner Color	White with red print	White with red print

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

