productinformation

tesa[®] 64956 800µm / 32mil double sided PE foam tape

tesa® 64956 is a double sided PE foam tape. The tape is equipped with a synthetic rubber adhesive.

tesa® 64956 features:

- Thickness: 800µm/31.5 mils
- Excellent immediate bonding strength
- High bonding strength even on low surface energy substrates
- Highly conformable foam backing provides high bonding strength on rough or uneven surfaces
- Multi-purpose tape suitable for hand or automatic application

Main Application

- Bonding of trims and profiles (plastic extrusions)
- Mounting of shelf edge labelling systems
- Fixing of cable channels
- Construction of POS-displays
- Mounting of indoor signs
- Assembly aid, pre-fixation

Technical Data

| | Backing material Color Total thickness Type of adhesive Elongation at break | PE foam black/white 800 μm 31.5 mils synthetic rubber 180 % | Tensile strength Type of liner Color of liner Thickness of liner | 8 N/cm 4.6 lbs/in glassine yellow 70 μm 2.8 mils |
|---|---|--|---|---|
| Δ | dhesion to | | | |

| A 1 | 1 | | | |
|-----|-----|-----|----|----|
| Δd | np | SIN | n | tο |
| Ad | IIC | 310 | 11 | ιU |
| | | | | |

| • | Steel (initial) | 15.0 N/cm | Steel (after 14 days) | 15.0 N/cm |
|---|-----------------|-------------|---|-------------|
| | | 137 oz/in | | 137 oz/in |
| | PC (initial) | 15.0 N/cm | PC (after 14 days) | 15.0 N/cm |
| | | 137 oz/in | | 137 oz/in |
| • | PE (initial) | 12.0 N/cm | PE (after 14 days) | 12.0 N/cm |
| | | 109.6 oz/in | | 109.6 oz/in |
| | PET (initial) | 15.0 N/cm | PET (after 14 days) | 15.0 N/cm |
| | | 137 oz/in | | 137 oz/in |
| | PP (initial) | 15.0 N/cm | PP (after 14 days) | 15.0 N/cm |
| | | 137 oz/in | | 137 oz/in |
| | PVC (initial) | 15.0 N/cm | PVC (after 14 days) | 15.0 N/cm |
| | | 137 oz/in | | 137 oz/in |

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



tesa® 64956 800µm / 32mil double sided PE foam tape

Properties

| • | Temperature resistance short term | 60 °C 140 °F | Resistance to chemicals Softener resistance | |
|----|---|-------------------|---|--|
| • | Temperature resistance long term | 40 °C 104 °F | Static shear resistance at 73,4 °F Static shear resistance at 104 °F | |
| • | Tack | ••• | | |
| | Ageing resistance (UV) Humidity resistance | •• | | |
| Εv | aluation across relevant tesa [®] assortme | nt: •••• very goo | d ●●● good ●● medium ● low | |

Additional Information

Liner variants:

PV06 red MOPP film (80µm/3.1 mils) н.

For latest information on this product please visit <u>http://l.tesa.com/?ip=64956</u>

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



great to work with